

IN THE CLAIMS

Please amend the claims as follows:

Claim 1 (Currently Amended): A ~~leather-like sheet for balls~~ ball at least a part thereof being made of an artificial leather comprising:

a fiber-entangled fabric and a porous surface layer disposed on a surface of the fiber-entangled fabric, the porous surface layer having a pattern formed by a plurality of outwardly projecting pebbles and valleys between the pebbles[[,]]; and

a plurality of microholes having an average diameter of 5 to 100 μm being formed on surfaces of the pebbles, but the microholes being substantially not formed on surfaces of the valleys.

Claim 2 (Currently Amended): The ~~leather-like sheet~~ ball according to claim 1, wherein an average spacing between adjacent microholes is 5 to 100 μm .

Claim 3 (Currently Amended): The ~~leather-like sheet~~ ball according to claim 1, wherein the microholes are formed on the pebbles in a density of 100 to 1,000/ mm^2 .

Claim 4 (Currently Amended): The ~~leather-like sheet~~ ball according to claim 1, wherein an average height difference between the pebbles and valleys in the pattern is 100 to 500 μm .

Claim 5 (Currently Amended): The ~~leather-like sheet~~ ball according to claim 1, wherein the microholes present on the pebbles are formed by buffing.

Claim 6 (Currently Amended): The ~~leather-like sheet~~ ball according to claim 1, wherein a softening agent is applied to at least surfaces of the pebbles on which the microholes are present.

Claim 7 (Canceled).

Claim 8 (New): The ball according to claim 6, wherein an amount of the softening agent applied to at least surfaces of the pebbles is 0.5 to 10 g/m² in terms of solid content.

Claim 9 (New): The ball according to claim 1, wherein a surface area of each pebble is 0.3 to 10 mm².

Claim 10 (New): The ball according to claim 1, wherein a surface area of each pebble is 0.5 to 5 mm².

Claim 11 (New): The ball according to claim 1, wherein the average diameter of microholes is 5 to 80 μm.

Claim 12 (New): The ball according to claim 1, wherein the average diameter of microholes is 7 to 60 μm.

Claim 13 (New): The ball according to claim 1, wherein the average diameter of microholes is 8 to 40 μm.

Claim 14 (New): The ball according to claim 1, wherein the average diameter of microholes is 8 to 35 μm .

Claim 15 (New): The ball according to claim 1, wherein the microholes are formed in a surface area of each pebble from the top to 50 μm below the top of each pebble.

Claim 16 (New): The ball according to claim 1, wherein the microholes are formed in a surface area of each pebble from the top to 40 μm below the top of each pebble.

Claim 17 (New): The ball according to claim 1, wherein the microholes are formed in a surface area of each pebble from the top to 30 μm below the top of each pebble.

Claim 18 (New): The ball according to claim 2, wherein the average spacing between adjacent microholes is 10 to 70 μm

Claim 19 (New): The ball according to claim 2, wherein the average spacing between adjacent microholes is 20 to 50 μm .